

## SealBoss® 4000 LV-Epoxy-Resin

### RANGE OF APPLICATION

- Structural Repairs
- Crack Injection and Gravity Feed in concrete, masonry, etc.
- Structural Joint Repair
- Welding Cracked Concrete
- Bolt Grouting
- Plate Grouting
- Delaminated Slab Welding
- Repairing Wood Beams

### TYPE OF MATERIAL

**SealBoss® 4000 LV-Epoxy-Resin** is a 100% solids, high modulus, low viscosity non-shrink two component epoxy resin that bonds to concrete and other surfaces.

**4000 LV-Epoxy-Resin**, Type I and II, Grade 2 Classes B and C for Epoxy Resin Adhesives.

**4000 LV-Epoxy-Resin** is an easy flow formulation for good penetration into cracks and voids even at lower injection pressures. The product is insensitive to moisture. Due to the high tensile and compressive strength of the cured product, **4000 LV-Epoxy-Resin** is ideal for structural repairs.

### PROCESSING

**4000 LV-Epoxy-Resin** is composed of two components. The mixing ratio by volume is 2:1 (A:B). Using our cartridge system either with a hand operated trigger gun or a convenient pneumatic or electric battery operated gun makes the application easy and clean. No matter how much material is dispensed the design of the gun will assure the correct mixing ratio. If a cartridge is not used up the plastic mixer needs to be replaced prior to the next use. Minimum surface temperature is 40F. Do not add solvents to the product.

### Surface Preparation

Surface must be clean and sound. It may be dry or damp, but free of standing water. Remove dust, grease, curing compounds, waxes, foreign particles and disintegrated materials. For bonding applications on concrete and steel surfaces sandblasting or other approved mechanical means are recommended.

### Various Applications

#### Gravity Feeding into Cracks

Pour material into vee-notched crack. Continue placement until completely filled. Seal underside if possible if cracks reflect through.

#### Crack Pressure Injection

Use automated or manual injection equipment. Set appropriate injection ports based on system used. Seal ports and cracks with **4000 QuickSeal** paste. When the epoxy seal has cured, inject resin with steady pressure. Consult additional data sheets and MSDS for further information.

## Low Viscosity Epoxy Resin Cartridge System Structural Repairs & Anchoring



### Slab Seal Application

Spread resin over slab and allow penetration. Remove excess to prevent surface film. Seal interior slabs and above grade exterior slabs only.

### Epoxy Mortar Use

Prime prepared surface with **4000 LV-Epoxy-Resin**. Place prepared epoxy mortar before primer becomes tack free. Place the epoxy mortar using trowels. Compact and level with vibrating screed or trowel. Finish with finishing trowel. Exterior application may darken with UV light exposure. Epoxy mortar can be mixed as follows: 1 gal **4000 LV-Epoxy-Resin** mixed with up to 5 gal of loose oven dried aggregate yields approx. 800 cu. inch of epoxy mortar. The gel time of pre-mixed material is determined by the quantity of the batch and the temperature. Since the reaction of the epoxy resin produces heat, a large batch is likely to react much faster than a small quantity of material.

### MAINTENANCE OF EQUIPMENT

Cartridge Systems are disposable and equipment maintenance is minimal. Remove all excess sealant and any smears. Tools and mixing equipment are best cleaned immediately after use. Solvents are hazardous, are aggressive towards plastic and rubber and might be in conflict with regulations on the jobsite. Caution! Some cleaners are combustible.

### PRECAUTION

Protect your health! While working with this material, safety goggles, gloves and safety clothing must be worn at all times. While injecting, a full face shield is strongly recommended. Spills and blow-outs do happen! Protect yourself and others on the jobsite. Consider property in proximity of the application area to prevent loss or damage. Protect your jobsite from unauthorized persons. Store all materials and equipment safely and out of reach of children! Observe container labels, MSDS, and instructions in the Product Catalog before using the product and equipment. In case one of the components comes in contact with the skin, wash thoroughly with soap and water. Provide adequate ventilation in volume and pattern in working area. Further protection: emergency showers and eyewash stations.

### STORAGE

Good storage stability of unopened containers at temperatures between 15-30C (58-85 F). Store indoors.

## SealBoss® 4000 LV-Epoxy-Resin

### Low Viscosity Epoxy Resin Cartridge System Structural Repairs & Anchoring

#### Injection Guns

We supply a wide selection of injection guns for use with the **4000 LV-Epoxy-Resin** Cartridge System. Systems are either manual, electric or pneumatic. Please see injection gun data sheets for more detailed information or call our technical support.



#### TECHNICAL DATA

	Comp. A	Comp. B	
Color	A/B Mixed	Amber/Grey/Black	
Solids	100%	100%	ASTM D 1010
Density, g/ml	1.14	0.93	ASTM D 3800-79
Mixing Ratio by Volume	2 parts	1 part	
Viscosity, cps	500	400	
Packaging	cartridge 34oz		
Viscosity mixed, cps	400-500		
Gel Time (C-881)	45 min.		
Pot Life (100 grams @77F)	30 min.		
Storage	Good storage stability for unopened containers at 15-30C 58-85F (1 yr). Store indoors.		
Cured Product			
Compressive Strength, psi (77F)	10,700 after 7 days		ASTM D-695
Bond Strength, psi	2,400 after 1 day		ASTM C-882
Bond Strength, psi	3,600 after 14 days		ASTM C-882
Tensile Strength, psi (77F)	7,000 after 14 days		ASTM D-638
Flexural Strength, psi	9,660		ASTM D-790
Shear Strength, psi	9,040		ASTM D-732
Bond Strength			
Concrete	Crack in Concrete		
Shrinkage	Passes		ASTM C-883
Heat Deflection Temperature	120F		ASTM D-648
<b>TYPE I, II, IV, V, GRADE 1</b>			<b>ASTM C-881-87</b>
<b>Classes B &amp; C</b>			
<b>Epoxy Resin Adhesive</b>			
Resistance to Chemicals	Resistant to Most Organic Solvents, Mild Acids, Alkali and Micro Organisms		

#### Important:

SealBoss Corp. **4000 LV-Epoxy-Resin** is a structural adhesive and has been tested in lab conditions. Structural strength and other properties in epoxy products are subject to many factors such as substrate temperatures and properties, UV-exposure, aging etc. It has to be considered that physical properties of the cured product in the application may vary based on the conditions.

**Limited Warranty Policy and Disclaimer for Products Supplied and/or Distributed by SealBoss Corp.:** All recommendations, statements and technical data herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty either expressed or implied. User shall rely on his or her own information and tests to determine suitability of the product for the intended use and user assumes all risk and liability resulting from his or her use of the product. Nothing contained in any supplied materials relieves the user of the obligation to read and follow the warnings and instruction for each product as set forth in the current Technical Data Sheet, product label and Material Safety Data Sheet prior to product use. SealBoss Corp. warrants supplied / distributed products to be free of manufacturing defects. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of the manufacturer which proves to be defective. There are no other warranties by SealBoss Corp. of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. SealBoss Corp. shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. SealBoss Corp. shall not be responsible for use of this product in a manner to infringe on any patent or any other intellectual property rights held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, UV damage, excessive temperature exposure, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and / or physical movement of the substrate or structural defects are also excluded from the limited warranty. SealBoss Corp. reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of or inability to use the product. Recommendations and statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller. SealBoss Corp. reserves the right to change the properties of products without notice.

Revised 201109