

## SealBoss® 6600 Vertical QuickFix

Two Component  
Flexible Polyurea Joint Repair System  
Vertical Applications  
Fast Concrete Joint Repairs

### DESCRIPTION

- ✓ 6600-Vertical QuickFix is a two component, rapid curing 1:1 ratio polyurea caulk designed for sealing vertical and horizontal joints.
- ✓ 6600 is used to fill interior control joints or new construction saw joints on vertical surfaces. 6600 can be used in exterior applications, where some joint movement from thermal cycling will occur.
- ✓ Standard color for 6600 is medium gray. Custom colors are also available. Please contact SealBoss for more information on custom colors.

### ADVANTAGES

- ✓ 100% Solids, Meets VOC Regulations
- ✓ Remains Flexible, Even in Cold Temperatures
- ✓ Available in custom colors
- ✓ Highly Moisture Insensitive
- ✓ Odorless, No Toxic Vapors
- ✓ Resistant to Petrochemicals

### TYPICAL APPLICATION ENVIRONMENTS

- |                                   |                                   |
|-----------------------------------|-----------------------------------|
| ✓ Industrial Facilities           | ✓ Airports                        |
| ✓ Warehouse Floors                | ✓ Water and Waste Water Treatment |
| ✓ Manufacturing Facilities        | ✓ Cold Storage Facilities         |
| ✓ Pulp and Paper Mills            | ✓ Food Processing Facilities      |
| ✓ Bottling and Canning Facilities | ✓ Freezers                        |

### APPLICATION

#### Procedure

Remove all debris, oil and/or other contamination from construction and saw joints. For best results re-cut joints with a dry diamond blade. If area to be caulked is wet or damp, joint must be primed with PU primer and allow to set to a slight tack.

#### Installation

Install caulk using a steady moderate flow of material, taking care not to stop material flow for more than twenty seconds.

### EQUIPMENT

SealBoss 6600-Vertical QuickFix can be applied by dual cartridge static mix guns or low pressure plural component static mix equipment. Contact SealBoss for specific equipment recommendations.

#### Pot Life

Pot life of 100g mass is three minutes @ 72°F. Higher temperatures and larger quantities will shorten pot life. Lower temperatures and smaller quantities will lengthen pot life.

#### Cure Time

Tack free in 5 minutes @ 72°F. Minimum age of concrete must be 21-28 days, depending on curing and drying conditions prior to applications.

#### Clean Up

Wipe up any excess 6600-Vertical QuickFix from concrete and tools before it cures. Once 6600 has cured use a sharp wall scraper to remove.

#### Tube Set Preparation

6600-Vertical QuickFix should be applied using the following procedures: remove the red safety cap and white plug exposing the open tube. Attach the static mixer to the cartridge set. Secure the static mixer to the cartridge set by tightening the retaining nut. Load the cartridge set into the dual position caulk dispenser. Dispense the material. Available work time is approximately thirty seconds.

#### Limitations

6600-Vertical QuickFix is not intended for exterior or interior joints that are subject to extreme movement. 6600 is a moisture sensitive product. Repair areas that are wet or damp must be primed. Contact SealBoss. for high movement joint fillers and sealers.

#### Packaging

- 300 x 300 dual cartridges
- 750 x 750 dual cartridges
- 5 x 5 gallon pails
- 5 x 15 gallon ponies
- 55 x 55 gallon drums
- 270 x 270 gallon totes

## SealBoss® 6600 Vertical QuickFix

**Two Component**  
**Flexible Polyurea Joint Repair System**  
**Vertical Applications**  
Fast Concrete Joint Repairs

### TECHNICAL DATA

#### Physical Properties

##### Hardness ASTM D-2240

Shore A 59-63  
Shore D 15-17

##### Tensile Properties ASTM D-412

Strength 264 psi  
Elongation 418%  
Abrasion Resistance Excellent  
Tear Strength ASTM D-624 98 pli  
Yield Strength ASTM D-412 76 psi  
Elastic Modulus ASTMD-412 618 psi

##### Solids

**Weight:** 100%  
**Volume:** 100%  
**Coverage** see chart

##### Viscosity

Poly Component 2230±500cps @ 77°F  
Iso Component 1278±300cps @ 77°F

##### Liquid Material Density & Specific Gravity

ISO (A) 9.21 lbs/gal  
(SG 1.106 g/ml)  
Poly (B) 8.96 lbs/gal  
(SG 1.076g/ml)

##### Toxicity

Contains polyisocyanate that may be irritating to the skin and is toxic if inhaled as particulate matter. Material contacting the skin should be neutralized by washing with generous amounts of water. At elevated temperatures or when spraying use a fresh air respirator.

##### Storage Stability or Shelf Life

6 months in unopened containers at 60°F to 90°F.

##### Application Guns

We supply pneumatic, electric & hand operated application guns.



#### Material Consumption

Filling joint slots in given dimensions.  
Feet achieved with 22 oz. Cartridge

Width (in.)	1/4"	1/2"	3/4"	1"	1-1/4"	1-1/2"
1/4"	52.9					
1/2"	26.5	13.2				
3/4"	17.6	8.8	5.9			
1"	13.2	6.6	4.4	3.3		
1-1/4"	10.6	5.3	3.5	2.6	2.1	
1-1/2"	8.8	4.4	2.9	2.2	1.8	1.5
1-3/4"	7.6	3.8	2.5	1.9	1.5	1.2
2"	6.6	3.3	2.2	1.6	1.3	1.1
2-1/2"	5.3	2.6	1.8	1.3	1.1	.87
3"	4.4	2.2	1.5	1.1	.87	.73

**Limited Warranty Policy and Disclaimer for Products Supplied and/or Distributed by SealBoss Corp.:** All recommendations, statements and technical data herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty either expressed or implied. User shall rely on his or her own information and tests to determine suitability of the product for the intended use and user assumes all risk and liability resulting from his or her use of the product. Nothing contained in any supplied materials relieves the user of the obligation to read and follow the warnings and instruction for each product as set forth in the current Technical Data Sheet, product label and Material Safety Data Sheet prior to product use. SealBoss Corp. warrants supplied / distributed products to be free of manufacturing defects. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of the manufacturer which proves to be defective. There are no other warranties by SealBoss Corp. of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. SealBoss Corp. shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. SealBoss Corp. shall not be responsible for use of this product in a manner to infringe on any patent or any other intellectual property rights held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, UV damage, excessive temperature exposure, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and / or physical movement of the substrate or structural defects are also excluded from the limited warranty. SealBoss Corp. reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of or inability to use the product. Recommendations and statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller. SealBoss Corp. reserves the right to change the properties of products without notice.

Revised 201012