

SealBoss Can-Seal-Foam™

Instant One Component Closed-Cell Polyurethane Foam up to 8 Gal Foam From 27oz Can

Professional Grade, Universal Use

THE Important Difference

SealBoss Can-Seal-Foam is engineered to fully expand inside the applicator 'gun barrel'. When the foam exits the tip of the gun it is almost fully expanded - you apply exactly as much foam as you need without the messy and undesired "mushrooming" experience you may have with most of the other 'over the counter' foam products. This feature makes our foam 'predictable' and useable in areas where other products just won't perform.

With our foam and the professional applicator gun you can fill voids precisely. Contractors use our foam for many applications such as water-stop purposes in voids and cable runs, as an insulation and seal-foam in general construction and as an instant 'Backer Rod Bead' in applications where joints need a back fill prior to applying the final sealant.

RANGE OF APPLICATION

- **Waterproofing:**
 - Cable Runs
 - Seals electrical conduits
 - Utility Boxes, etc.
 - Seals around pipes/ducts
- **Increases energy efficiency**
- **Reduces noise**
- **Controls radon**
- **Seals out insects**
- **Confines fibers**
- **Strengthens tub bases**
- **Seals stressskin panels**
- **Upgrades weatherization**
- **Repairs boat flotation**
- **Seals refrigeration panels**

FEATURES

- Professional Control Steel Gun Applicator
- Ozone Friendly
- High Volume From Small Can

BENEFITS

- No Cleaning
- Low Cost
- Unlimited Start Ups and Closures

VOLUME

- 8 to 9 gal Foam
- 1800 Cu. inches
- 1/2" Bead runs 900 lin. ft.

TYPE OF MATERIAL

Can-SealFoam is a closed cell self curing foam for universal uses. The product is a single component MDI based polyurethane of highest quality. It expands, bonds and seals while stopping the passage of air, gases, water and dust. Besides its obvious uses to stop water infiltration it can increase energy efficiency by stopping air exchange around windows, doors, wall intrusions and at sill plates. Its lightweight, closed cell structure makes it useful for deadening sound, flotation and thermal insulation. It is also useful for scaling work areas prior to stripping to prevent the transport of fibers.

Can-SealFoam is very efficient, you get up to eight gallons pf foam just from one can!

Insulation Value: The product has an R-Value of about 4 to 8 depending on the thickness of the bead.

Sound: STC = 69

Can-SealFoam & Professional Gun sold separately

SealBoss Corp. 1669 E Wilshire Ave, Santa Ana, CA 92705 Toll Free 877-932-2293 Ph 714-662-4445 Fax 714-662-4446
e-mail: info@SealBoss.com info@webac.com Internet: www.SealBoss.com www.webac.com

webac.com®
online information service



Store Like This

Use Like This



SealBoss Can-Seal-Foam™

Instant One Component Closed-Cell Polyurethane

HOW TO USE:

1. Shake the can of foam.
2. Thread the can into the adapter on the top of the gun - DO NOT OVER TIGHTEN.
3. Pull the trigger for about 5 seconds to purge all air and moisture out of the gun.
4. Wipe or mist water into the joint which is to be foamed.
5. Select the bead size by interacting between the trigger and the flow adjustment screw.
6. The can should be in a vertical position over the gun when foaming.
7. Remove uncured foam from the end of the dispensing tube after each use. Tighten the flow adjustment screw for storage.
8. To replace an empty can, unscrew it and promptly screw a replacement can into the adapter. If no replacement is available, leave the empty can in place until a replacement is at hand.

ALWAYS KEEP A CAN OF FOAM ON THE GUN. FAILURE TO DO THIS WILL ALLOW FOAM TO CURE AND RESULT IN PERMANENT DAMAGE TO THE GUN.

Best Results:

Use in warm weather

1. Shake the can for 30 seconds.
2. Layout practice beads.
3. To enhance cure time you may mist the area with water.

Use in cold weather

1. Warm the can to room temperature 60F-80F
2. Layout practice beads.
3. To enhance cure time you may mist the area with water.

In all conditions it is advised to mist in between layers of foam if a high fill volume is desired. The moisture will help the foam to cure and prevent it from collapsing in high volume applications.

CHANGING CANS

1. With the canister on its base and the gun nozzle pointing into a suitable container, squeeze the trigger until the rest of material and gas is discharged.
2. Unscrew the can from the gun and wipe off any foam residue from around the ball valve housing with a small amount of suitable solvent.
3. Fit a new canister as described above. Purge out air.
4. Do not remove an empty can from the gun until you have a new can to replace with.

CAUTION

Due to possible production off highly flammable vapor and air mixtures, provide sufficient ventilation. Do not smoke while using the product. In case of eye contact, rinse with plenty of water and seek medical attention. In case of skin contact wash off with plenty of water and soap. Wear suitable protective gloves and goggles during work. In case of accident, or if you feel unwell, seek immediate medical attention. Container is pressurized. Protect from sunlight and temperatures above 50C, Do not pierce or burn even if can seems to be empty. Do not spray against flames or onto incandescent objects. Harmful when inhaled, irritates eyes, respiratory organs and skin, Can result in sensitization when inhaled. Can produce highly flammable vapor and air mixtures during use.

PRODUCT CONTENT

Polyol prepolymer CAS 59675-67-1,4,4'

Monomeric diphenyl methane diisocyanate (MDI)

CAS 101-68-8

Chlorodifluoroethane CAS 75-68-3.

MDI can irritate eyes, respiratory organs and skin.

PROPERTIES OF CURED FOAM

Color: Yellowish
Expanded volume: Free rise at 68% relative humidity 8-9 gals, ~180cu.inches

Density: 1.2 Lbs/cu ft
Cell Structure: Closed, 80%
Compression load
deflection: 10% compr. 8.5Lbs/sq. in.
Minimum can temp: 40F, 5C
Min. surface temp 32F, 0C
Temperature stability
cured foam: -40F to 176F, -40C to 80C
Tack free at 68F, 20C 15 min
Cuttable at 68F, 20C 30 min

Flammability test
ASTM E 84
Flame spread index: 25
Smoke density: 210
Class 1: Fire rating construction
Thermal resistance
R factor ASTM C 518: 5.0/in.
STC Rating 69
Can Size: 27oz.

Limited Warranty Policy and Disclaimer for Products Supplied and/or Distributed by SealBoss Corp.: All recommendations, statements and technical data herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty either expressed or implied. User shall rely on his or her own information and tests to determine suitability of the product for the intended use and user assumes all risk and liability resulting from his or her use of the product. Nothing contained in any supplied materials relieves the user of the obligation to read and follow the warnings and instruction for each product as set forth in the current Technical Data Sheet, product label and Material Safety Data Sheet prior to product use. SealBoss Corp. warrants supplied / distributed products to be free of manufacturing defects. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of the manufacturer which proves to be defective. There are no other warranties by SealBoss Corp. of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. SealBoss Corp. shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. SealBoss Corp. shall not be responsible for use of this product in a manner to infringe on any patent or any other intellectual property rights held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, UV damage, excessive temperature exposure, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and / or physical movement of the substrate or structural defects are also excluded from the limited warranty. SealBoss Corp. reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of or inability to use the product. Recommendations and statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller. SealBoss Corp. reserves the right to change the properties of products without notice.

Revised 201001