

SealBoss® FlexLiner

INDUSTRIAL LINER / MEMBRANE Flexible Elastomeric, Aromatic Polyurethane Coating System

SYSTEMTYPE & DESCRIPTION

SealBoss Flex Liner is a two component liquid applied, asphalt blended aromatic polyurethane. The applied product consists two coats of FlexLiner with an optional polyester inner-ply mat, called a scrim. The system adheres well to most substrates. The Liner is very durable and its monolithic surface structure will provide long term waterproofing if applied correctly. The elastomeric properties permit the system to expand and contract with normal structural movements. The **Flex Liner** System offers a wide range of uses in commercial and residential applications.

OUTSTANDING FEATURES

- Seamless Waterproofing Membrane
- Bridges cracks and joints
- Impervious to water & most aqueous chemicals
- VOC Compliant
- Very Economical
- UV Stable, color appearance may change

TYPICAL USES

- Waterproofing
- Tank Liner
- Pond Liner
- Containment
- Roofing (with scrim)
- Reservoirs (with scrim)
- Ponds (with scrim)
- Corrosion Protection

COMMONSUBSTRATES

- Concrete
- Steel
- Glass
- Wood
- Metal
- Asphalt

COLOR

Black. Can be top coated with **TopCoat**

COMMONSUBSTRATES

- Asphalt
- Concrete
- Steel
- Metal

MIXING

Proportions are premeasured. The mix ratio is 1:9 A:B by volume. Using a mechanical mixer, pre-mix **Flex Liner** Part-B material thoroughly to obtain a uniform color. Use care not to allow air into the mixture. **Flex Liner** should not be mixed by hand.

PRIMING

Most substrates should be primed with recommended primer.

APPLICATION

Apply two coats of **Flex Liner** at 2 gallons per 100 sq. ft. each coat directly to a clean dry substrate.

Do not apply product at surface temperatures below 50° F (10° C). Also temperature must be 5° F (3° C) above dew point.

Do not apply when the ambient or substrate temperature is rising.

Do not apply product in direct sunlight.

Spray equipment, squeegee, notched trowel or phenolic resin core roller may be used; if a roller is used extra care should be taken not to trap air bubbles into the mixture. Apply Flexliner evenly over the entire deck at 58 wet mils. Most applications require only one coat, but if needed FlexLiner may be re-coated in 1 hour. If FlexLiner has cured for more than 8 hours, the surface may need to be mechanically abraded and cleaned before re-coating.

RE-COAT

Re-coating/Multiple or Second coats must be completed within eight (8) hours of previous applications of **Flex Liner**. After this eight (8) hour window, it is necessary to abrade, clean and prime surface prior to Re-coating.

Abrasing shall be by grinder or other mechanical means.

CURING

At 70° F (21° C) and 50% relative humidity, allow coating to cure for 24 hours for light traffic, or 72 hours for heavy traffic.

Flex Liner FL-IM 19 is sensitive to heat and moisture and this could accelerate the curing time.

EQUIPMENTCLEANUP

Equipment should be cleaned with mineral spirits or an environmentally safe solvent, as permitted under local regulations, immediately after use.

STORAGE

Flex Liner FL-IM 19 has a shelf life of one (1) year from the date of manufacture in original, factory-sealed containers.

SCRIM

Recommendation: 18 GAUGE SOFT FINISH STITCH BONDED POLYESTER FABRIC REINFORCEMENT MATERIAL.

See reverse side for Technical Data and other pertinent information.

SealBoss® FlexLiner

INDUSTRIAL LINER / MEMBRANE Flexible Elastomeric, Aromatic Polyurethane Coating System

LIMITATIONS

Do not apply **Flex Liner** in wet weather or if rain is imminent. Coating should not become wet within 4 hours after application. Containers that have been opened must be used as soon as possible.

If substrates are not clean and dry, **Flex Liner** will not achieve good adhesion and the coating over concrete may blister.

Concrete/asphalt: The outside temperature should be in a declining mode (installation should be done in the late afternoon).

New concrete/asphalt and masonry must be cured for 28 days.

UV stable but the color may fade, chalk and discolor over time.

The following must not be coated with **Flex Liner**: concrete over an un-vented metal pan, magnesite and lightweight concrete.

Equipment should be cleaned with an urethane grade environmentally safe solvent, as permitted under local regulations, immediately after use.

Uncured materials are sensitive to heat and moisture.

A non-continuous application defies a monolithic surface.

The substrate must be structurally sound and sloped for proper drainage.

WARNINGS

This product contains Isocyanates, Asphalt and Solvent.

Technical Data

Coverage Rate @1 gal/100 sq.ft.	14.25mils
Pot Life @75F (24C), 50% RH.	approx. 20 minutes
Hardness, ASTM D-2240	~ 60 A
Tear Resistance, Die C, ASTM D-624	150 (+- 50)pli, ~26.3 kN/m
Tensile Strength, ASTM D-412	~ 900psi, 6.2MPa
Ultimate Elongation, ASTM D-412	450 +-100%
Total Solids by Volume, ASTM D-2697	89%
Volatile Organic Compounds	0.73lb/gal
ASTM D-2369-81	87.5gm/liter

Limited Warranty Policy and Disclaimer for Products Supplied and/or Distributed by SealBoss Corp.: All recommendations, statements and technical data herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty either expressed or implied. User shall rely on his or her own information and tests to determine suitability of the product for the intended use and user assumes all risk and liability resulting from his or her use of the product. Nothing contained in any supplied materials relieves the user of the obligation to read and follow the warnings and instruction for each product as set forth in the current Technical Data Sheet, product label and Material Safety Data Sheet prior to product use. SealBoss Corp. warrants supplied / distributed products to be free of manufacturing defects. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of the manufacturer which proves to be defective. There are no other warranties by SealBoss Corp. of any nature whatsoever expressed or implied, including any warranty of merchantability or fitness for a particular purpose in connection with this product. SealBoss Corp. shall not be liable for damages of any sort, including remote or consequential damages resulting from any claimed breach of any warranty whether expressed or implied. SealBoss Corp. shall not be responsible for use of this product in a manner to infringe on any patent or any other intellectual property rights held by others. In addition, no warranty or guarantee is being issued with respect to appearance, color, fading, chalking, staining, shrinkage, peeling, UV damage, excessive temperature exposure, normal wear and tear or improper application by the applicator. Damage caused by abuse, neglect and lack of proper maintenance, acts of nature and / or physical movement of the substrate or structural defects are also excluded from the limited warranty. SealBoss Corp. reserves the right to conduct performance tests on any material claimed to be defective prior to any repairs by owner, general contractor, or applicator. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss or damage directly or indirectly resulting from use of or inability to use the product. Recommendations and statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller. SealBoss Corp. reserves the right to change the properties of products without notice.

Revised 2011-3